

Claim 4 (original): The catalyst according to claim 1 comprising Ag and at least one of Zn or Bi.

Claim 5 (currently amended): The catalyst according to claim 1 wherein said catalyst is supported on a support which is highly porous having average pore diameter larger than about 180Å, no pores narrower than 35 Å, total pore volume larger than about 0.65 cc/g, and ~~preferably less than about 100 m²/g~~ BET surface area less than about 100 m²/g.

Claim 6 (original): The catalyst according to claim 1 comprising K.

Claim 7 (original): The catalyst according to claim 1 wherein Pd is in the range of 0.005 to 1% by weight; Ni is in the range of 0.0 to 15% by weight; Ag is in the range of 0.002 to 20% by weight; Zn is in the range of 0 to 5% by weight and Bi is in the range of 0 to 5% by weight.

Claim 8 (original): The catalyst according to claim 1 wherein Pd is in the range of from 0.01% to 0.3% by weight; Ni is in the range of from 0 to 10% by weight; Ag is in the range of 0.005 to 5% by weight; Zn is in the range of 0.002 to 1% by weight and Bi is in the range of 0.01 to 3% by weight.

Claim 9 (currently amended): The catalyst according to claim 6 wherein the content of K is less ~~that~~ than 0.5 % by weight.

Claim 10 (original): The catalyst according to claim 5 wherein said support is alumina having a BET surface area of 10 to 100 m²/g.

Claim 11 (original): The catalyst according to claim 10 wherein said support has